

Bayblend® FR3010 HF

Polycarbonate + ABS

Covestro - Polycarbonates

PROSPECTOR®

www.ulprospector.com

Technical Data

Product Description

(PC+ABS)-Blend; flame retardant; easy flowing; Vicat/B 120 temperature = 108°C; UL recognition 94 V-0 at 1.5 mm; glow wire temperature (GWI): 960°C at 2.0 mm; optimized processability; good light stability

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• Flame Retardant		
Features	• Flame Retardant • Good Flow	• Good Processability • UV Resistant	
RoHS Compliance	• RoHS Compliant		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density (73°F (23°C))	1.18 g/cm ³	1.18 g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (240°C/5.0 kg)	1.53 in ³ /10min	25.0 cm ³ /10min	ISO 1133
Spiral Flow ^{2, 3}	15.7 in	40.0 cm	Internal Method
Molding Shrinkage ⁴			ISO 2577
Across Flow : 464°F (240°C), 0.118 in (3.00 mm)	0.50 to 0.70 %	0.50 to 0.70 %	
Flow : 464°F (240°C), 0.118 in (3.00 mm)	0.50 to 0.70 %	0.50 to 0.70 %	
Water Absorption			ISO 62
Saturation, 73°F (23°C)	0.50 %	0.50 %	
Equilibrium, 73°F (23°C), 50% RH	0.20 %	0.20 %	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus (73°F (23°C))	377000 psi	2600 MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield, 73°F (23°C)	8700 psi	60.0 MPa	
Break, 73°F (23°C)	7250 psi	50.0 MPa	
Tensile Strain			ISO 527-2/50
Yield, 73°F (23°C)	4.0 %	4.0 %	
Break, 73°F (23°C)	> 50 %	> 50 %	
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact Strength			ISO 180/A
-22°F (-30°C)	4.8 ft·lb/in ²	10 kJ/m ²	
73°F (23°C)	17 ft·lb/in ²	35 kJ/m ²	
Unnotched Izod Impact Strength (73°F (23°C))	No Break	No Break	ISO 180
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Heat Deflection Temperature			
66 psi (0.45 MPa), Unannealed	212 °F	100 °C	ISO 75-2/B
264 psi (1.8 MPa), Unannealed	194 °F	90.0 °C	ISO 75-2/A
Vicat Softening Temperature			
--	223 °F	106 °C	ISO 306/B50
--	226 °F	108 °C	ISO 306/B120
CLTE			ISO 11359-2
Flow : 73 to 131°F (23 to 55°C)	4.2E-5 in/in/°F	7.6E-5 cm/cm/°C	
Transverse : 73 to 131°F (23 to 55°C)	4.4E-5 in/in/°F	8.0E-5 cm/cm/°C	



Bayblend® FR3010 HF

Polycarbonate + ABS

Covestro - Polycarbonates**PROSPECTOR®**

www.ulprospector.com

Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	1.0E+16 ohms	1.0E+16 ohms	IEC 60093
Volume Resistivity (73°F (23°C))	1.0E+16 ohms-cm	1.0E+16 ohms-cm	IEC 60093
Electric Strength			IEC 60243-1
73°F (23°C), 0.0394 in (1.00 mm)	890 V/mil	35 kV/mm	
Relative Permittivity			IEC 60250
73°F (23°C), 100 Hz	3.20	3.20	
73°F (23°C), 1 MHz	3.10	3.10	
Dissipation Factor			IEC 60250
73°F (23°C), 100 Hz	4.0E-3	4.0E-3	
73°F (23°C), 1 MHz	7.0E-3	7.0E-3	
Comparative Tracking Index (Solution A)	350 V	350 V	IEC 60112

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Flame Rating			UL 94
0.06 in (1.5 mm)	V-0	V-0	
0.09 in (2.2 mm)	5VB	5VB	
0.12 in (3.0 mm)	5VA	5VA	

Additional Information	Nominal Value (English)	Nominal Value (SI)
ISO Shortname	PC+ABS-FR(40)	PC+ABS-FR(40)

Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature - Dry Air Dryer	176 °F	80 °C
Drying Time - Dry Air Dryer	4.0 hr	4.0 hr
Suggested Max Moisture	< 0.020 %	< 0.020 %
Suggested Shot Size	30 to 70 %	30 to 70 %
Rear Temperature	428 to 446 °F	220 to 230 °C
Middle Temperature	437 to 455 °F	225 to 235 °C
Front Temperature	446 to 464 °F	230 to 240 °C
Nozzle Temperature	491 to 509 °F	255 to 265 °C
Processing (Melt) Temp	464 to 518 °F	240 to 270 °C
Mold Temperature	140 to 194 °F	60 to 90 °C
Back Pressure	725 to 2180 psi	5.00 to 15.0 MPa
Vent Depth	9.8E-4 to 3.0E-3 in	0.025 to 0.075 mm

Injection Notes

Peripheral Screw Speed: 0.05 - 0.2 m/s
Standard Melt Temperature: 260°C
Hold Pressure (% of Injection Pressure): 50 - 75%

Notes

- ¹ Typical properties: these are not to be construed as specifications.
- ² Mold Temperature: 176°F (80°C), Melt Temperature: 500°F (260°C)
- ³ 2x8mm
- ⁴ 150x105x3mm,, MT 80°C



Bayblend® FR3010 HF

Polycarbonate + ABS

Covestro - Polycarbonates

PROSPECTOR®

www.ulprospector.com

Where to Buy

Supplier

Covestro - Polycarbonates

Leverkusen, Germany

Telephone: +49-214-6009-2000

Web: <http://www.plastics.covestro.com/>

Distributor

ALBIS Plastic

ALBIS Plastic is a global distribution and compounding company. Contact ALBIS Plastic for availability of individual products per country.

Telephone: +49-40-78105-0

Web: <http://www.albis.com/>

Availability: Algeria, Austria, Belgium, China, Czech Republic, Denmark, Estonia, Finland, France, Germany, Hong Kong, Hungary, Ireland, Latvia, Lithuania, Luxembourg, Morocco, Netherlands, Norway, Poland, Portugal, Romania, Russian Federation, Slovakia, Spain, Sweden, Switzerland, Tunisia, Turkey, United Kingdom

Amco Polymers

Telephone: 800-262-6685

Web: <http://www.amcopolymers.com/>

Availability: North America

M. Holland Company

Telephone: 855-497-1403

Web: <http://www.mholland.com/>

Availability: Mexico, United States

PolyOne Distribution

PolyOne Distribution is a global distribution company. Contact PolyOne Distribution for availability of individual products by country.

Telephone: 800-894-4266

Web: <http://polyonedistribution.com/>

Availability: Global

Reseller

A Reseller is not a distributor authorized by the Supplier.

Shanghai Jingyang New Material Technology Co., Ltd

Telephone: +86-021-80394788; Mr. Zhou: +86-15821998203

Web: <http://www.basfppsu.com/>

Availability: Asia Pacific, China

